



Thinky Application Datasheet 1

Ceramic and Water (10 V %) THINKY Mixing Time - 2 minutes

Materials: (1) Barium Titanate (BaTiO_3) + (2) Dispersion retaining agent (3) Tap water
Capacity: Total 150g
Density: Barium Titanate - 6.02 g/cm³
Material Ratio: Barium Titanate - 10 volume %
THINKY Mixer: ARE-250

Hand Mixing - 2 minutes	THINKY Mixing - 2 minutes
	
There are large agglomerates X 1000	No agglomerates can be observed. Powder dispersed evenly through water. X1000