

Thinky Application Datasheet 9

Zinc Oxide powder (10 Vol. %) in petroleum Jelly

THINKY Mixing Time - 3 minutes

THINKY DefoArming Time - 3 minutes

Materials: Zinc Oxide (powder) + petroleum Jelly (semi solid)

Specific Gravity: petroleum Jelly 0.85, Zinc Oxide 5.76

Capacity: Total 100g (ZnO 10v%)

THINKY Mixer: Vacuum-less ARE-250

Container: Disposable cup 150cc



After mix, the surface is like mirror,
Don't see any agglomeration on the bottom side.

Disperse completely into Jelly with no air bubble
Microscope x100